

# FLUORITZ<sup>®</sup>-HT101



Sticking strength is lower than competitive material and has good chlorine gas resistance

## Typical property

Color	Hardness (Shore A)	Tensile strength (MPa)	Elongation (%)	100% modulus (MPa)	Service temperature range (°C)	Compression set (%)
Black	82	12.5	130	8.9	260	17

Compression Set: After squeezing 25% at 200°C x 72 hours  
Above values are actual measurements, not standards.

## Feature

Radical resistance  
Chlorine gas resistance

## Application

Semiconductor and LCD  
Chemical industry  
Electrical & Electronics industry

All trademarks and registered trademarks noted in this file are the exclusive property of Nippon Valqua Industries, Ltd. unless otherwise specified. This document is made for use in Japan. Although these data are created based on the data and the information of December 2012, Nippon Valqua Industries Ltd. may change these data without notice for the reason of improvement in functional of a product, standard revision and others. Please note the following point in use of these data. (1) An operating temperature, pressure range, durability, etc. indicated in this catalogue do not assume each operation conditions but show the application possibility based on our company data, an actual result, etc. Therefore, please use these data after checking the aptitude in actual use environment. (2) The data contained within this catalogue can only be taken as a guide. (3) A standard, a value, etc. are the purposes made legible, and may be performing an extract, recombination, arrangement, conversion, etc. of a value. (4) Although the maximum attention was paid in this data creation, Nippon Valqua Industries Ltd. will not accept responsibility for any loss incurred through error or omission. Please contact your distributor or VALQUA group if you have any questions. (5) This document contains confidential information. So please do not disclose this confidential information to the third party without our company's permission.

© 2012 Nippon Valqua Industries, Ltd. All rights reserved.  
Manufactured in Japan.



**NIPPON VALQUA INDUSTRIES., Ltd.**  
<http://www.valqua.co.jp>

## Contact:

**NIPPON VALQUA INDUSTRIES., Ltd.**  
ThinkPark Tower, 1-1, Osaki 2-chome,  
Shinagawa-ku, Tokyo, 141-6024, Japan  
Tel: +81-3-5434-7380, Fax: +81-3-5436-0566